

Bjelin Woodura Planks 3.0

Hardwax oil

Level of use domestic: **EN ISO 10874** Class Heavy Residential (Class 23)*



Level of use commercial: **EN ISO 10874** Class Very Heavy Commercial (Class 34)*



Woodura	Hardened Wood
Construction	Engineered wood surface with cured wood composite core and wood backing
Surface treatment	Hardwax oil

General properties	XL	XXL
Thickness (mm)	11	11
Width (mm)	206	271
Length (mm)	2200	2378
Wear layer thickness (mm)	0,6	0,6
Micro bevel	long- and short side	long- and short side
Locking system	5G Dry	5G Dry
Boards per box	4	3
m ² per box	1,8	1,9
m ² per pallet	87	93
Weight per m ² (kg)	11	11
Weight per box (kg)	20	22

Classification and safety properties	Standard test method	Result
Fire resistance	EN 13501	Bfl-S1 (hardly flammable)
Thermal conductivity	EN 12664	0,16 W/(m x K)
Thermal resistance	EN 12667	0,07 (m ² x K)/W
Formaldehyde emission	EN 717-1	E1
Brinell hardness	EN 1534	10 HB (mv)
Impact resistance	EN 14354	EC3
Thickness swelling	EN 14354	<8%
Wear resistance	Not applicable	Not applicable
Slip resistance	Not applicable	Not applicable
Step sound reduction when using 2 mm underlay foam	EN ISO 10140-3 EN ISO 717-2	18-20 dB

Installation properties	
Installation method	Floating or glue down application
Installation instructions	Download from www.bjelin.com
Underlayment	Foam with CS > 60 kPa & CC > 20 kPa (according to EN 16354)**
Care & maintenance Instructions	Download from www.bjelin.com

* Oiled products are suitable for any area with correct refurbishment

** For demanding applications



woodura™



The mark of responsible forestry
FSC® C140726

